

MAXDAN

MAXDAN is stable bituminous emulsion and doughy consistency. Composed of bituminous tiny particles in a water solution, containing an inert colloid, which permanently ensures the stability of the product. When the water solution evaporates, the MAXDAN emulsion turns into a bituminous film.



TECHNICAL DATA

TECHNICAL DATA	VALUE	UNIT	STANDARD
Relative density at 20°C	0,9-1,1	g/cm ³	-
Water content	45 ± 5	%	-
Colour	Black	-	-
Toxicity	Null	-	-
Flammability	Null	-	-
Drying time (20-25 °C and 50% of relative humidity)	24	h	-
Application temperature	+ 5	°C	-
Output	0.5	Kg/m ² by layer	-

PRESENTATION

PRESENTATION	VALUE	UNIT
Cans	25 / 5	kg
Output	0.5	kg/m ²
Product Code	311033 / 311032	-

HANDLING, STORAGE AND CONSERVATION

- This product is not toxic and non-flammable.
- Will be stored in a dry place protected from rain, Sun, heat, and cold temperatures. Temperatures below 0 ° C can affect the quality of the product. With these conditions and their tightly closed source packaging, the product can remain stored approximately six months from the date of manufacture.
- The product will be used in order of arrival to work.
- In all cases, standards of safety and hygiene at work, as well as standards of good practice of the construction must be taken into account.
- In case of sedimentary material, it must be removed to return to the initial state.
- Danosa recommend consult the safety data sheet of this product which is permanently available at www.danosa.com, or you can request in writing to our technical department.
- For any further clarification, please consult with our Technical Department.

WARNING

The information that appears in the following document makes reference to the uses and utilities of danosa's products and systems, and it is based on the knowledge that have been learnt until present, by Danosa. This is only possible if products have been stored and used in an appropriate way.

Nevertheless, Danosa is not responsible for unsuitable uses of the products neither any other facts, such as meteorological facts. So Danosa is just responsible for the quality related to the provided products. Danosa reserves the right to carry out modifications without previous notice.

The values that appear in the technical sheet are the results of the tests that have been performed in our laboratory. July 2014.

Web site: www.danosa.com E-mail: export@danosa.com Phone number: +34 949 888 210